

No.7, Thiruverkadu Main Road, Near Ambattur Industrial Estate, Ayappakkam, Chennai-600 077 Tamilnadu State-South India Ph No.91-044-26820071 Cell No.9444007960 **E-mail: contact@pentagonchemical.com Website: www.pentagonchemical.com**

POTASSIUM SILICATE : TECHNICAL DATA

Our POTASSIUM SILICATE k-66, K-76 and K-120 Grades are fully filtered and does not contain any Impurities like un reacted, suspended silica etc., Our material does not coagulate, as it is free of Sodium silicate and other impurities, its ionization potential (i.e. getting more viscous due to Absorption at atmospheric carbon dioxide) is very low.

CONTENT	K-66	K-76	K NEUTRAL
K2O	10.75 - 11.75	12.5 - 13.5	10.0 - 10.50
Na2O	Traces	Traces	Traces
SiO2	21.5 - 23.5	26.0 - 28.5	21.0 - 22.10
SPG	1.32 - 1.37	1.37 - 1.39	1.30 - 1.31
CHLORIDE	0.2 MAX	0.2 MAX	0.2 MAX
A 11 / 1 1			

SEPCIFICATION

All the above percentages by weight.

For **PENTAGON CHEMICALS**

-SDS-Authorized Signatory